

X-Tech EpoxySeal FLR110

Chemical resistant high build epoxy floor coating

Product Description

X-Tech EpoxySeal FLR110 is a high performance, high build, solvent free epoxy floor coating that is also decorative and suitable for use in a wide range of applications. It can also be used as a wall coating.

Advantages

- High abrasion resistance
- Resistant to wide range of chemicals
- Smooth and anti-slip finish available
- Easy to clean and maintain

Uses

- Car park decks
- Process areas
- Pharmaceutical, food and beverage plants
- Storage areas
- Stairwells

Specification Compliance

SCAQMD Rule 1113
LEED NC2009 IEQ 4.2
FDA CFR 21 Section 175.300
EFNARC Type 3A
FeFRA Type 3 MD

Laboratory Test Data

Property	Typical Results
Compressive strength (ASTM D695)	>58MPa
Flexural strength (BS EN196)	>29MPa
Abrasion resistance (ASTM 4060)	194mg loss/1000 cycles
Impact resistance (ASTM D2794)	No cracking
Bond to concrete (BS 1881)	>2MPa

Volatile Organic Content

X-Shield SF Primer = <50g/L
X-Shield MT Primer = <50g/L X-Tech
EpoxySeal FLR110 = <50g/L

Application Properties

Application thickness (2 coats)	300 to 400 microns
Application temperature range	10 to 35C (50 to 95F)
Pot life at 25c X-Shield SF Primer X-Shield MT Primer X-Tech EpoxySeal FLR110	30 mins 120 mins 40 mins
Recoat time	18 to 24 hours at 25c
Full cure	7 days at 25C

Chemical Resistance

X-Tech EpoxySeal FLR110 has excellent resistance to the following chemicals:

White spirit
20% Sulphuric acid
Concentrated bleach
Saturated sugar solution

Oils
Petrol

Colors

RAL 7001 Silver Grey
RAL 6029 Mint Green
RAL 7035 Light Grey
Others colours available on request.

RAL 5017 Traffic Blue
RAL 1001 Beige
RAL 3002 Carmine Red

Theoretical Coverage

X-Tech EpoxySeal FLR110: 5 to 6.6 m²/Liter per coat.
Wet film thickness of 150 to 200 microns/m²
Actual coverage will depend on wastage and surface profile and can be up to 20% or more higher than theoretical coverage.

Packaging

X-Tech EpoxySeal FLR110: 1 and 5 Kg pack.

Shelf Life

18 months when stored below 30C under shade in a dry environment.

Installation Guidelines

X-Tech EpoxySeal FLR110 should be applied by experienced coating crews. NCC X-Calibur provides detailed method statements on all its products for use in various applications. These must be referred to prior to starting work. The information below is a summary intended for guidance only.

Surface Preparation

The substrate must be structurally sound. Loose or unsound concrete should be removed and made good. Surfaces must be entirely free of oil, grease, paint, corrosion deposits, dust, laitance or other surface deposits. The surface should be prepared by captive blasting to produce a lightly exposed aggregate surface i.e. a ICRI CSP 4 or 5 surface profile. Any bug holes (blow holes) should be filled with X-Shield BugFill or X-Shield Primer Filler (when using X-Shield MT Primer apply BugFill or Primer Filler after priming). If substrate is not level or is uneven, level using X-Tech LevelCem HD.

Moisture Testing

The concrete slab should be tested for moisture with the Rapid RH system following the procedure in ASTM F2170. If the humidity reading is greater than 80% then conduct moisture vapor emission rate (MVER) testing using the procedure in ASTM F1869. (Both test kits are available for purchase from X-Calibur). If the MVER Primer is 3 to 5 lbs/1000ft²/24h use a single coat X-Shield MT Primer at 165 microns wft. If the MVER is 5 to 12 lbs/1000ft²/24h use two coats of X-Shield MT Primer at 200 microns wft per coat.

Priming

Prime with X-Shield SF Primer or X-Shield MT Primer and allow to dry before applying X-Tech EpoxySeal FLR110. The base and hardener have to mixed using a slow speed drill and approved mixing paddle until homogenous. The mixed primer should then be applied to the prepared substrate with a polyurethane squeegee and back rolled with a short hair roller (NCC X-Calibur velvet roller or similar). Do not over apply or allow puddles of primer to form. If the primer is absorbed into the surface easily, it will be necessary to apply a second coat once the initial coat is tack-free. Allow the primer to become tack-free before application of X-Tech EpoxySeal FLR110. Apply X-Tech EpoxySeal FLR110 within the recoat window.

Mixing

Add the hardener to the base and mix using a slow speed drill with an X-Shield Coating Mixer. Paddle for 3 minutes until both components have fully dispersed and are uniform in color. Be sure to rotate the mixer throughout the drum. Mix only full packs.

Application

Apply in two coats of 150 to 200 microns per coat (6 to 8mils) wet film thickness using short hair roller (X-Calibur velvet roller or similar) or airless spray. Recoat after 18 to 24 hours at 25C

Slip Resistant Finish

A slip resistant finish can be achieved by broadcasting X-Tech Anti Skid Grains onto the surface of the first coat while still wet. The grain size (Fine, Medium or Coarse) and broadcast rate will depend on the surface texture required but will generally be in the range of 0.5 to 1kg/m².

Limitations

May change color when exposed to direct sunlight.
Do not be apply within 3C of the dewpoint or if it is within 5C of the dewpoint and dropping.
Avoid excessive application.
Avoid skin contact.
Do not apply below 10C.
Do not discard into the water system.
Protect from chemical and water spillage until fully cured.

Health and Safety

This product is for industrial use only by trained operatives. It is potentially hazardous if not used correctly. Please refer to the Material Safety Data Sheet (MSDS) prior to the purchase and use of this product. The MSDS can be obtained via our website www.ncc.com.eg

Authorized Technical Specialist

Please note that only NCC X-Calibur Authorized Technical Specialists ('ATSS') are permitted to change any of the information in this data sheet or to provide written recommendations concerning the use of this product. Visit www.ncc.com.eg for a full list of NCC X-Calibur ATSS.

Datasheet Validity

NCC X-Calibur makes modifications to its product datasheets on a continuous basis. Please check the datasheet update section on www.ncc.com.eg to ensure you have the latest version.

Warranties

NCC X-Calibur supplies products that comply with the proper-ties shown on the current datasheets. In the unlikely event that products supplied are proved not to comply with these properties, then we will replace the non-compliant product or refund the purchase price. X-Calibur does not warrant or guarantee the installation of the products as it does not have control over the installation or end use of the products. Any suspected defects must be reported to NCC X-Calibur in writing within five working days of being detected. NCC X-Calibur Construction Systems **makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties express or implied.** NCC X-Calibur Construction Systems Inc. shall not be liable for damages of any sort including remote or consequential damages, down time, or delay.