

X-Shield AntiCarb S

Anti-carbonation coating for concrete

Product Description

X-Shield AntiCarb S is a medium performance anti-carbonation coating that is decorative and can provide resistance to chloride ingress when used in conjunction with an X-Shield Anti-Chloride treatment.

Composition

X-Shield AntiCarb S is a water-dispersed, solvent free, acrylic co-polymer coating containing fillers, pigments, adhesion promoters and wetting agents.

Advantages

- Good carbonation resistance
- Breathable
- Non-flammable
- Environmentally friendly
- Available in wide range of colors
- Can be used with anti-chloride treatments
- Contains anti-fungal and anti-bacterial additives

Uses

- Anti-carbonation coating
- Decorative coating
- Anti-chloride coating

Specification Compliance

Classified under BS EN 1062-1:2002 as a Grade C₁ anti-carbonation coating for concrete.

Laboratory Test Data

Property	Typical Results
Water vapor transmission rate	>150g/m ² .d
Liquid water permeability	<0.1 to 0.5 kg/m ² .h ^{0.5}
Carbon dioxide permeability	>50m ^{air} at DFT 160 Micron
Crake Bridge (ASTM C836)	0.3 mm
Pull off (N/mm ²)	3.5 MPa

Color

Standard: Grey (BS 10A03) and white.
Other colors available on request subject to minimum order.

Finish

Smooth matt.

Theoretical Coverage

5.7m² per liter per coat.

Packaging

25 Kg drums.

Shelf Life

12 months when stored below 35C (95F) under shade in a dry environment.

Installation Guidelines

X-Shield AntiCarb E should be applied by experienced paint crews. NCC X-Calibur provides detailed method statements on all its products for use in various applications. These must be referred to prior to starting work. The information below is a summary intended for guidance only.

Surface Preparation

The substrate must be structurally sound. Loose or unsound concrete should be removed and made good. Surfaces must be entirely free of oil, grease, paint, corrosion deposits, dust, laitance or other surface deposits. The surface should be prepared by light grit blasting or high pressure water blasting to produce a lightly exposed aggregate surface. Any bug holes should be filled with a cementitious or acrylic filler.

Priming

Prime the surface with X-Shield Primer AR. This product should be used on cement render, plaster substrates and concrete with a high alkali or cement content. In areas subject to high chloride concentrations, prime using an X-Shield Anti-Chloride treatment.

Application

Apply in two coats of 120 micron (4.8mils) wet film thickness using brush, roller or airless spray. When using airless spray, tip size should be 0.017" to 0.0020" at a pressure of 2200psi. The product can be thinned by 5%, if necessary, using clean water but the wet film thickness should be increased accordingly. Recoat after 2 to 4 hours at 30C (86F). Clean equipment using water.

Limitations

Do not use in immersed conditions.
Do not apply below 5C (41F).
Avoid excessive application.
Avoid skin contact.
Do not discard into the water system.
Apply only on to slabs that have a waterproofing system installed in order to prevent blistering due to osmosis.

Health and Safety

This product is for industrial use only by trained operatives. It is potentially hazardous if not used correctly. Please refer to the Material Safety Data Sheet (MSDS) prior to the purchase and use of this product. The MSDS can be obtained via our website www.ncc.com.eg

Authorized Technical Specialist

Please note that only NCC X-Calibur Authorized Technical Specialists ('ATs') are permitted to change any of the information in this data sheet or to provide written recommendations concerning the use of this product. Visit www.ncc.com.eg for a full list of NCC X-Calibur ATs.

Datasheet Validity

NCC X-Calibur makes modifications to its product datasheets on a continuous basis. Please check the datasheet update section on www.ncc.com.eg to ensure you have the latest version.

Warranties

NCC X-Calibur supplies products that comply with the properties shown on the current datasheets. In the unlikely event that products supplied are proved not to comply with these properties, then we will replace the non-compliant product or refund the purchase price. NCC X-Calibur does not warrant or guarantee the installation of the products as it does not have control over the installation or end use of the products. Any suspected defects must be reported to NCC X-Calibur in writing within five working days of being detected. NCC X-Calibur Construction Chemicals. **makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties express or implied.** NCC X-Calibur Construction Chemicals. shall not be liable for damages of any sort including remote or consequential damages, down time, or delay.



CERTIFICATE NO: 50926